

# webermur gletofix

## INDOOR SKIMMING COMPOUND

### *Area of application*

May be applied on surfaces based on lime, cement, cement-lime plaster and concrete at least one month old and plaster cardboard panels, in areas where high humidity is not expressed. It is suitable as a base for applying interior paints, decorative techniques and for gluing wallpaper.

webermur gletofix is a thin-layer skimming compound for fine leveling of interior walls and ceilings, based on lime and high-quality filler, enriched with polymers. It is characterized by bright whiteness, excellent processing and firm adhesion to the surface.

Product benefits:

- Bright whiteness
- Excellent adhesion
- High vapor permeability
- Easy application

Product classification:

CS I Wc0 A1 (EN 998-1:2016)



## Surface preparation

The base on which the product is applied on must be clean, solid, dry, without traces of oil and grease, supported and without parts falling off. Insufficiently supported coatings and parts that are falling off, should be fully removed and repaired using appropriate material, and disinfected surfaces contaminated with algae or fungi with a suitable agent before applying the leveling compound. In case of stains occurring due to rain or impurities from smoke, it is necessary to repair and block further penetration of impurities to the surface, prior to applying the skimming compound.

Coat the surfaces with a suitable primer in order to neutralize dust, regulate absorbency and improve adhesion, at least 12 hours before applying the skimming compound. A suitable primer for gypsum plasterboards and plaster that does not fall off is weberprim base, diluted with pure water in a ratio of 1:8. Very absorptive and old surfaces, concrete surfaces and mechanical mortar with an open structure that is falling off (uncoated or unsmoothed mortar) must be stabilized with weberprim deep primer diluted with pure water in a ratio of up to 1:6.

## Product use and installation

1. Pour 25 kg (5kg) of skimming compound into 9-10 l (1.8-2 l) of pure water and stir with electric mixer to the bottom of the bucket, until the material becomes homogenous. After stirring, leave the webermur gletofix to stand for 5-10 minutes, and then stir again to make the material ready for use. It is not allowed to dilute the compound with an excessive amount of water.
2. Apply the prepared homogenized compound with a stainless steel trowel in two to three layers. In the first layer, apply the compound in a thickness of 1-2 mm, so that the surface is completely covered. Carry out the sanding so that the structure is as smooth as possible, preferably without tool marks and unevenness. If the surface is visible after the first application, repeat the application procedure fresh on fresh or only after drying, in order to achieve the thickness of the coating. The maximum total coating thickness is 4mm.
3. Drying of the first layer takes at least 12 hours in optimum weather conditions. Before applying the second layer, it is necessary to prepare the first layer by removing excess skimming compound with a spatula or fine sandpaper with 150-240 grit (manually or by machine), as well as by completely dusting the surface.
4. Apply the second layer over the fully dried first layer in a thickness of about 1 mm, carefully align the compound so that the surface is flat, smooth and without defects. The drying of the second layer lasts at least 12 hours before further processing. If necessary, apply a third layer of skimming in a thickness of about 1 mm for the final leveling of the surface.
5. It is necessary to prepare the dried plastered surface before applying dispersion paint, decorative technique or gluing wallpaper. The preparation should be done by removing excess skimming manually or by machine, with 150-240 grit sandpaper, depending on the requirements for surface smoothness, no earlier than 24 hours after application. When sanding, make sure that the final layer of skimming compound is not completely removed (match the sanding paper and the speed of the machine). In the case of the above mentioned, apply again a layer of skimming compound repeating the procedure. The surface finished with the skimming compound must be smooth, level and dusted before applying the primer and the final layer (paint, decorative technique, wallpaper).
6. The mixed skimming compound may be used in a bucket for 3 days from the moment of mixing. In order to prevent the formation of a crust, cover the surface of the mixed material with pure water or PE film in contact with the mixed material.

\*All stated parameters refer to standard weatherconditions: temperature 20°C, relative humidity up to 65%.

7. Prilikom ugradnje i sušenja temperatura podloge i vazduha mora iznositi između 5°C i 30°C. Ukoliko vremenski uslovi nisu u skladu sa standardnim, potrebno je postupak rada obustaviti i sačekati da se steknu optimalni uslovi. Sušenje proizvoda može trajati duže pri nižoj, odnosno kraće po višoj temperaturi vazduha i podloge, a takođe zavisi i od vlažnosti vazduha i upojnosti podloge.

The manufacturer recommends application on small, test surfaces to make sure the product/surface are properly prepared and that appropriate conditions for use and installation have been provided. If not, please stop the work and contact the Saint-Gobain građevinski proizvodi d.o.o. Beograd company representative. The company shall not be responsible for incorrect execution of works with the stated material as well as use of material for the purpose not stated in product description. Complaints submitted after the completion of execution of shall not be accepted.

### Tools

For mixing: electric mixer or manually.  
For application: steel trowel, spatula.  
For processing: sandpaper (150-240 grit).

### Product consumption

About 1.0 kg/mm/m<sup>2</sup>.  
The consumption may vary depending on the conditions whereunder the applying of smooth coat is performed and the characteristics of the surface whereon the skimming compound is applied.

### Keeping, storage and transport

Product webermur gletofix must be stored in original, undamaged packaging, on solid and functional pallets, in dry space, without direct exposure to snow, rain, hail and sun, protected from frost, in closed or covered space.

The product is not hazardous for transport in the sense of all national and international transport regulations. During transport, the product must be protected from the elements. Transport and store the product at temperature from +5°C to +30°C.

### Product safety

Hazardous compound ingredients: Hydrated limestone 5-10%



**Danger**

Causes skin irritation. Causes serious eye damage. Keep out of reach of children. Wash hands thoroughly after handling. Wear protective gloves/protective clothing/face protection. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If skin irritation occurs: Get medical advice/attention. Take off contaminated clothing and wash it before reuse. Dispose of contents and container in accordance with RS regulation.

## Technical characteristics of the product

Product color: webermur gletofix is a white-colored skimming compound.

Packaging: 25 kg sodium sack, 1200 kg on a pallet; 5 kg sodium sack, 1000 kg on a pallet.

Expiration date: 12 months from the production date pressed on the packaging.

Detailed information on product, additional documentation and safety data sheet are available on the official webpage [www.rs.weber](http://www.rs.weber).

## Cleaning

Residue of fresh product can be cleaned from the tools and surfaces with water. Hardened product must be removed only mechanically.

## Product limitations

webermur gletofix skimming compound cannot be used in the following situations:

- With wooden and metal surfaces.
- With insufficiently supported surfaces
- With surfaces containing impurities
- In premises with high humidity
- By mixing it with impure water and other additives
- At temperatures for storage, transport, application and drying lower than +5°C and higher than +30°C.

## Environment

Unused product and empty packaging may not be disposed outside of waste management locations. See safety data sheet of the product for more information.

## Disposal method

Disposal of content and packaging in line with local regulations. Dispose the packaging and unused material separately. Do not allow penetration into the sewerage system. Do not dispose together with municipal waste.

## Country of origin and product manufacturer:

Country of origin: Republic of Serbia

Manufacturer: Saint-Gobain građevinski proizvodi d.o.o. Beograd, 115d Bulevar Mihajla Pupina Street, 5th floor, 11070 Novi Beograd, Republic of Serbia. Contact telephone: 011 314 96 81.



**SAINT-GOBAIN GRAĐEVINSKI  
PROIZVODI D.O.O. BEOGRAD**

115d Bulevar Mihajla Pupina Street,  
V floor 11070 • Novi Beograd • Serbia  
Tel.: + 381 11 314 96 84  
[info.rs@saint-gobain.com](mailto:info.rs@saint-gobain.com)  
[www.saint-gobain.rs](http://www.saint-gobain.rs)

Technical information stated herein as well as recommendations are based on our knowledge and experience in cases when the product is properly stored, used, transported and when handled in regular conditions. The buyer, or the user of the product is advised to test the product, if it is suitable for use for intended purpose. Considering the fact, we do not have influence on the circumstances of product use and handling, we shall not be liable for consequences occurring from irregular use. The buyer, or the user of the product shall be liable in case the product is kept, transported, installed and used contrary to instructions, purpose and properties and information on product safety, as well as after stated expiration date for product use. Our team of experienced experts provides advice in phases of planning and application of our products. Visit to the construction site and demonstration of application of our products may be organized at request. Contact our technical team and find out more on our products on the website [www.saint-gobain.rs](http://www.saint-gobain.rs).